



## Apex® 8DSR

**DESCRIPTION:** Ladle and furnace brick, resin bonded, made with predominantly fused grain. Very high erosion and slag resistance. Good oxidation resistance due to high-purity flake graphite. Antioxidants can be added.

**USES INCLUDE:** Electric furnace hotspots.  
Electric furnace sidewalls.  
Ladles.  
BOF working linings.

### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

|                                |       |
|--------------------------------|-------|
| MgO                            | 98.0% |
| CaO                            | 1.0%  |
| SiO <sub>2</sub>               | 0.8%  |
| Fe <sub>2</sub> O <sub>3</sub> | 0.2%  |
| Al <sub>2</sub> O <sub>3</sub> | 0.1%  |

### TYPICAL AS RECEIVED PROPERTIES:

|   |              |
|---|--------------|
| Antioxidants:   | Can be added |
| Apparent Porosity (%):  | 2.5          |
| Bulk Density, original g/cm <sup>3</sup> (lb/ft <sup>3</sup> ): | 3.00 (187)   |
| Carbon (%):   | 5.0 – 20.0   |
| Crushing Strength psi (MPa):                                    | 6000 (41)    |

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11