



INFORMATION BULLETIN

Flosan® 300Z

DESCRIPTION: Mixture of carefully selected and processed refractory materials with a high sintering point. Made with high-purity zircon.

USES INCLUDE: Nozzle filler for sliding gates ladle system.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

| | |
|--------------------------------|-------|
| Cr ₂ O ₃ | 31.0% |
| Fe ₂ O ₃ | 17.6% |
| SiO ₂ | 11.2% |
| Al ₂ O ₃ | 10.0% |
| Zircon | 21.5% |
| MgO | 6.6% |
| C | Yes |

TYPICAL AS RECEIVED PROPERTIES:

Shipped in either 3000 lb. super sacks, 1000 lb. drums, 50 lb. bags, or 25 lb. bags.

Other packing options may also be available.

Store pallets in a dry and protected area.

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 25.02