



INFORMATION BULLETIN

Icon® 4

DESCRIPTION: Magnesia alumina carbon brick, resin bonded, with very high erosion and slag resistance. With antioxidants.

USES INCLUDE: Electric furnace sidewalls.
Ladle barrel and/or bottoms.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % by weight)

MgO	84.0%
Al ₂ O ₃	11.0%
Fe ₂ O ₃	1.9%
CaO	1.3%
SiO ₂	1.3%

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity (%):	~ 3.0
Bulk Density, Orig g/cm ³ (lb./ft ³):	3.0 (187)
Cold Crushing Strength (psi):	6000
Carbon (%)	5.0 - 20.0

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11
