

INFORMATION BULLETIN

Icon® 6

DESCRIPTION: Magnesia alumina carbon brick, resin bonded, made

with fused grain. Very high erosion and slag resistance. Good oxidation resistance due to high-

purity flake graphite. With antioxidants.

USES INCLUDE: Electric furnace hotspots and sidewalls.

Ladle furnace slaglines.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS - after ignition)

(Approximate % by weight)

 $\begin{array}{ccc} \text{MgO} & 86.0\% \\ \text{Al}_2\text{O}_3 & 10.0\% \\ \text{CaO} & 1.0\% \\ \text{SiO}_2 & 1.0\% \\ \text{Fe}_2\text{O}_3 & 0.7\% \\ \end{array}$

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity (%): 2.5

Bulk Density, Orig g/cm³ (lb./ft³): 3.0 (187) Cold Crushing Strength (psi): 6000 Carbon (%): 5.0 - 20.0

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11

Phone: 1-800-609-5711 www.FRCglobal.com