



## INFORMATION BULLETIN

### Icon®

---

**DESCRIPTION:** Magnesia alumina carbon.

**USES INCLUDE:** Ladle barrels and bottoms.

### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % by weight)

MgO	78.0%
Al <sub>2</sub> O <sub>3</sub>	10.0%
C	7.0%

### TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity (%)	< 5.0
Bulk Density, original g/cm <sup>3</sup> :	3.0
Cold Crushing Strength (psi):	> 8000

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11

---

Phone: 1-800-609-5711  
[www.FRCglobal.com](http://www.FRCglobal.com)