



Ladlemag®

DESCRIPTION: Backfill based on synthetic forsterite for low density and high refractoriness. Dust-free with a binder.

USES INCLUDE:

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % by weight)

MgO	45.0 - 55.0%
SiO ₂	35.0 - 45.0%
Fe ₂ O ₃	5.0 - 7.0%
Others	1.0 - 2.0%
Na ₂ O(SiO ₂)x(H ₂ O)x	0.0 - 5.0%
Al ₂ O ₃	< 2.0%
CaO	< 2.0%
L.O.I.	< 1.0%

TYPICAL AS RECEIVED PROPERTIES:

Bulk Density pcf (g/cc):	85 (1.36)
Standard Size (mesh):	40

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11
