



Apex 8

DESCRIPTION: Electric furnace ladle and furnace refractory containing predominantly fused grain and high-quality graphite. Antioxidants can be added.

USES INCLUDE: Electric furnace hotspots.
Electric furnace sidewalls.
Ladles.
BOF working linings.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

MgO	98.0%
CaO	1.0%
SiO ₂	0.8%
Fe ₂ O ₃	0.2%
Al ₂ O ₃	0.1%

TYPICAL AS RECEIVED PROPERTIES:

Antioxidants:	Can be added
Apparent Porosity (%):	2.5
Bulk Density, original g/cm ³ (lb/ft ³):	3.00 (187)
Carbon (%):	5.0 - 20.0
Crushing Strength (psi):	6000

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11
