

## INFORMATION BULLETIN

## Epic® 40

**DESCRIPTION:** High-duty fireclay brick made from high-quality

clays. Made only from 88% minimum purity Bauxite.

**USES INCLUDE:** Boiler tile.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

 $Al_2O_3$   $\geq 40.0\%$   $TiO_2$   $\leq 2.8\%$   $Fe_2O_3$   $\leq 2.0\%$ 

## TYPICAL AS RECEIVED PROPERTIES:

Bulk Density (g/cm $^3$ ): > 2.15 Cold Crushing Strength (MPa): > 25.4 Apparent Porosity (%):  $\leq$  24.0

Reheat Change (%):

@ 1300/2 hrs +0.1, -0.4

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 23.11

Phone: 1-800-609-5711 www.FRCglobal.com