



INFORMATION BULLETIN

Epic® 55 C30Z6

DESCRIPTION: High-density alumina chrome brick.

USES INCLUDE: High wear areas in molten metal applications.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

Al ₂ O ₃	55.0%
Cr ₂ O ₃	30.0%
ZrO ₂	6.5%
SiO ₂	4.5%
P ₂ O ₅	1.6%
Fe ₂ O ₃	0.5%

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity (%):	15.0
Bulk Density (g/cm ³):	3.47

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11