



## Epic® 80C

---

**DESCRIPTION:** A burned alumina brick based on Bauxite and fortified with chrome ore to provide improved slag resistance. Chrome levels to meet customer demands but 3 and 5% are standard.

**USES INCLUDE:** EAF roof brick.  
Ladle linings.  
Kiln brick where aggressive atmospheres persist.

### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

Al <sub>2</sub> O <sub>3</sub>	80.0%
Fe <sub>2</sub> O <sub>3</sub>	< 5.0%
Cr <sub>2</sub> O <sub>3</sub>	3.0 - 5.0%

### TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity (%):	22.0
Bulk Density pcf (g/cm <sup>3</sup> ):	184 (2.75)
Cold Crushing Strength psi (MPa):	8700 (60)

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11