

## INFORMATION BULLETIN

## Fedcast 92

**DESCRIPTION:** Low-moisture castable made from high-purity

alumina.

USES INCLUDE: Ladle lips.

Precast shapes where high refractoriness is required.

## CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

 $\begin{array}{cccc} \text{Al}_2\text{O}_3 & & & \text{91.2\%} \\ \text{SiO}_2 & & & \text{6.0\%} \\ \text{CaO} & & & \text{2.5\%} \\ \text{MgO} & & & \text{0.1\%} \\ \text{TiO}_2 & & & \text{0.02\%} \\ \text{Fe}_2\text{O}_3 & & & \text{0.03\%} \\ \text{Alk} & & & \text{0.02\%} \end{array}$ 

## TYPICAL AS RECEIVED PROPERTIES:

Temperature	Bulk Density	Cold Crushing Strength	Cold MOR	Linear Change
°C (°F)	pcf (g/cc)	psi (MPa)	psi (MPa)	%
149 (300)	181 (2.90)	15,000 (103)	2250 (15)	0.0
815 (1500)	180 (2.88)	14,000 (96)	1900 (13)	- 0.1
1538 (2800)	178 (2.85)	11,000 (75)	4250 (29)	+ 0.2
1649 (3000)	185 (2.96)	16,000 (110)	5250 (36)	- 0.1

Material Installed Weight pcf (g/cc):180 (2.88)

Maximum Grain Size (mesh): 4

Recommended Water Range: 5.5 - 6.0 Service Temperature °C (°F): 1816 (3300)

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11

Phone: 1-800-609-5711 www.FRCglobal.com