



Icon 5

DESCRIPTION: Magnesia alumina carbon brick, resin bonded, with very high erosion and slag resistance. With antioxidants.

USES INCLUDE: Electric furnace sidewalls.
Ladle/furnace bottoms.
BOF working linings.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % by weight)

MgO	85.0%
Al ₂ O ₃	10.0%
Fe ₂ O ₃	1.9%
CaO	1.0%
SiO ₂	1.0%

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity (%):	2.5
Bulk Density, Orig g/cm ³ (lb./ft ³):	3.0 (187)
Cold Crushing Strength (psi):	6000
Carbon (%)	5.0 - 20.0

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11
