



Icon

DESCRIPTION: Magnesia alumina carbon.

USES INCLUDE: Ladle barrels and bottoms.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % by weight)

MgO	78.0%
Al ₂ O ₃	10.0%
C	7.0%

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity (%):	< 5.0
Bulk Density, original g/cm ³ :	3.0
Cold Crushing Strength (psi):	> 8000

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11