



## INFORMATION BULLETIN

### Jefrit 85

---

**DESCRIPTION:** Repair mix, used for hot repair of EOP lining, produced from DBM.

**USES INCLUDE:** Repair Mix.

#### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

MgO	83.0% minimum, 85.0% typical
Fe <sub>2</sub> O <sub>3</sub>	7.8%
CaO	7.0%
SiO <sub>2</sub>	1.5%

#### TYPICAL AS RECEIVED PROPERTIES:

Application Method:	Throwing
Bonding Type:	Ceramic
Grain Size (mm):	0.0 - 8.0
Storage Limit (months):	6
Temp Limit for Application (°C):	1750

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11

---