



## Jetmag

---

**DESCRIPTION:** Excellent flow characteristics for easy installation. The material is based on synthetic forsterite which provides both low density for low thermal conductivity and good refractoriness.

**USES INCLUDE:** Ladle backfill material.

### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % by weight)

MgO	45.0 - 55.0%
SiO <sub>2</sub>	35.0 - 45.0%**
Fe <sub>2</sub> O <sub>3</sub>	5.0 - 7.0%
Others	1.0 - 2.0%
Al <sub>2</sub> O <sub>3</sub>	< 2.0%
CaO	< 2.0%
L.O.I.	< 1.0%

\*\*More than 99% of the silica is chemically linked to magnesium.

### TYPICAL AS RECEIVED PROPERTIES:

Standard Size (mesh): 40

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11

---