



## Paragon RDM6

---

**DESCRIPTION:** Dolomite brick with resin bonded and graphite.

**USES INCLUDE:** Ladle brick material.

### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

MgO	55.0%
CaO	43.0%
Residual Carbon	6.0%
SiO <sub>2</sub>	0.6%
Fe <sub>2</sub> O <sub>3</sub>	0.5%

### TYPICAL AS RECEIVED PROPERTIES:

Bulk Density (g/cm <sup>3</sup> ):	2.88
Cold Crushing Strength (N/mm <sup>2</sup> ):	70
Required Material (kg/dm <sup>3</sup> ):	4.0%

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 24.01

---