

## INFORMATION BULLETIN

## Epic® AC

**DESCRIPTION:** Resin-bonded alumina carbon brick.

**USES INCLUDE:** Iron ladle working linings.

## CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

 $\begin{array}{cccc} AI_2O_3 & 90.0\% \\ C & 10.0\% \\ SiO_2 & 6.0\% \\ TiO_2 & 3.9\% \\ Fe_2O_3 & 1.0\% \end{array}$ 

## TYPICAL AS RECEIVED PROPERTIES:

Antioxidants AL Apparent Porosity (%): 4.0

Bulk Density pcf (g/cm<sup>3</sup>): 200 (3.20) Cold Crushing Strength psi (MPa): 10,900 (75)

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11

Phone: 1-800-609-5711 www.FRCglobal.com